


# Textured Polyester & Nylon Multifilament Yarns

## For Embolization Coil Device Applications



*The textured yarns are solvent cleaned and steam-set to produce an open yarn bundle. The softly crimped filaments separate to aid in the occlusion of blood vessels when attached to embolization coils.*

Item	Titer <sup>1</sup> (Denier)	Filaments	Tenacity <sup>2</sup> (g/d)	Elongation (%)	Net Wt. (g)	Length (m)	Package Type
<b>30/34-PA66-FTT-SCS</b>	30	34	4.2	16	~6-12	~1800-3600	Bobbin
<b>40/34-PA66-FTT-SCS</b>	40	34	4.2	16	~6-12	~1400-2700	Bobbin
<b>50/24-PET-N401-FTT-SCS</b>	50	24	4.2	16	~6-12	~1000-2000	Bobbin

1. Titer Conversion:  $Dtex = Denier \times 1.1111$
2. Tenacity Conversion:  $cN/dtex = g/d \times 0.8826$

**DISCLAIMER:** The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the material are responsible for assuring that it is suitable for their needs, environment and end use. All data is subject to change as TDA deems appropriate.