

















# Polypropylene Monofilament Knitted Mesh Fabrics

For Biomedical Applications

Consider Polypropylene Mesh for...  
Surgical Mesh  
Hernia Mesh  
Incontinence Slings  
Vaginal Prolapse Suspension  
Pelvic Floor Reconstruction  
Tissue Carrier

Style	Mono-filament Dia. mm (in)	Typical Pore Size mm (in)	Burst Strength kPa (psi) (ASTM D-3786)	Break Strength N/2.5 cm (lbs/in) (ASTM D-5034)		Break Elongation (%) (ASTM D-5034)		Thick. mm (in) (ASTM D-1777)	Wt. g/m <sup>2</sup> (oz/yd <sup>2</sup> ) (ASTM D-3776)
				MD	CMD	MD	CMD		
<b>PPKM403</b> 	0.10 (.004)	1.3 X 1.0 (.051 X .039)	585 (85)	228 (51)	220 (49)	77	118	0.43 (.017)	47 (1.4)
<b>PPKM404</b> 	0.10 (.004)	0.9 X 0.8 (.035 X .031)	510 (74)	129 (29)	182 (41)	142	90	0.36 (.014)	41 (1.2)
<b>PPKM405</b> 	0.10 (.004)	1.6 X 1.4 (.063 X .055)	363 (53)	184 (41)	158 (36)	82	62	0.38 (.015)	33 (1.0)
<b>PPKM408</b> 	0.10 (.004)	0.7 X 0.7 (.028 X .028)	433 (63)	145 (33)	120 (27)	100	105	0.33 (.013)	34 (1.0)
<b>PPKM409</b> 	0.10 (.004)	1 X 1.5 (.039 X .059)	519 (75)	254 (57)	165 (37)	78	116	0.38 (.015)	44 (1.3)
<b>PPKM411</b> 	0.10 (.004)	3.0 X 2.7 (.118 X .106)	244 (35)	100 (22)	79 (18)	48	50	0.41 (.016)	22 (0.6)
<b>PPKM501</b> 	0.125 (.005)	1.3 X 1.1 (.051 X .043)	716 (104)	301 (67)	236 (53)	70	130	0.51 (.020)	63 (1.8)
<b>PPKM502B</b> 	0.125 (.005) Blue	1.3 X 1.2 (.051 X .047)	875 (127)	305 (68)	275 (62)	88	103	0.50 (.020)	66 (1.9)

Style	Mono-filament Dia. mm (in)	Typical Pore Size mm (in)	Burst Strength kPa (psi) (ASTM D-3786)	Break Strength N/2.5 cm (lbs/in) (ASTM D-5034)		Break Elongation (%) (ASTM D-5034)		Thick. mm (in) (ASTM D-1777)	Wt. g/m <sup>2</sup> (oz/yd <sup>2</sup> ) (ASTM D-3776)
				MD	CMD	MD	CMD		
<b>PPKM503</b> 	0.125 (.005)	1.0 X 0.6 (.039 X.024)	930 (134)	311 (70)	336 (76)	70	110	0.46 (.018)	65 (1.9)
<b>PPKM505</b> 	0.125 (.005)	1.2 X 1.5 (.047 X.059)	688 (100)	320 (72)	233 (52)	66	105	0.43 (.017)	58 (1.7)
<b>PPKM506BS</b>  Blue Stripe	0.125 (.005)	1.7 X 1.6 (.067 X.063)	491 (71)	245 (55)	169 (38)	70	100	0.43 (.017)	46 (1.4)
<b>PPKM601</b> 	0.15 (.006)	1.3 X 1.0 (.051 X.039)	1063 (154)	516 (116)	485 (109)	94	137	0.61 (.024)	100 (2.9)
<b>PPKM604</b> 	0.15 (.006)	1.0 X 1.2 (.039 X.047)	670 (97)	320 (72)	205 (46)	80	120	0.52 (.020)	64 (1.9)
<b>PPKM605</b> 	0.15 (.006)	1.0 X 0.6 (.039 X.024)	750 (108)	300 (67)	340 (76)	165	90	0.51 (.020)	80 (2.3)
<b>PPKM607BS</b>  Blue Stripe	0.15 (.006)	3.0 X 2.2 (.118 X.087)	590 (86)	280 (63)	195 (44)	66	96	0.53 (.021)	44 (1.3)
<b>PPKM608B</b>  Blue	0.15 (.006)	1.4 X 1.4 (.055 X.055)	1000 (145)	400 (90)	330 (74)	72	105	0.63 (.025)	84 (2.5)

**DISCLAIMER:** The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the material are responsible for assuring that it is suitable for their needs, environment and end use. All data is subject to change as TDA deems appropriate. If cuts or slits are created in our polypropylene mesh fabrics in the machine (warp) direction during the fabrication process or by the end user, it is advisable to place a stitch at the end of the cut to prevent it from separating further. Certain styles of our polypropylene mesh fabrics may be more prone to this. Please contact us if you have any questions or concerns regarding this.